

0.85 E.S. Sand

Size range 0.7 – 1.5mm

Application

Used in water filtration. From natural uncrushed raw material which is washed, dried and accurately screened and is free of any friable or agglomerated grains.

The sand will be resistant to degradation during normal handling, placing and commissioning works.

Characteristics

Colour: Tan

Appearance: Sub-angular to rounded Specific Gravity: Approx 2.6tonnes/m³
1.6tonnes / m³

Hardness: 7 Moh

Mechanical Analysis - Grading Envelope

Sieve Size	% Passing	Typical % Passing
2.0	98-100	99
1.7	95-100	98
1.4	50-90	85
1.18	30-80	50
1.0	10-30	18
0.85	5-15	10
0.71	0-5	2

Effective Size 0.80-0.90mm Uniformity Coefficient ≤ 1.50

Silica Content - 95%

ISSUE DATE JUNE 2019

www.irwin-aggregates.com

Irwins Quality Aggregates 55 Gortgonis Road, Coalisland, Co. Tyrone, BT71 4QG Tel: 028 87 740362 Fax: 028 87 747473