

Page 1 of 4
Report Number: 2017-753-1759

Prepared for: Irwins Quality Aggregates Ltd

55 Gortgonis Road

Coalisland Co Tyrone BT71 4QG

Sample described as: Play Sand

No. of samples: 1 Reference number(s): 6032

**Date received:** 30/06/17 **Date(s) tested:** 06/07/17-20/07/17

**Declared age grade:** Not stated **Packaging:** None

Client specified age grade: Not stated

I certify that the above mentioned sample has been tested in accordance with the standard(s) specified below and that it complies or otherwise as follows:

EN 71-3:2013+A1:2014

Complies

Please see attached report AR-17-JR-013742-02 for report details

Stag

Claire Francis

Gillian Kay

Senior Analytical Services Manager Analytical Services Manager

Date: 21st July 2017



Subcontracted to an ILAC accredited laboratory within Eurofins The reported results relate exclusively to the tested sample

**Eurofins Product Testing Services Limited** 

Dunham House, Cross Street, Sale, M33 7HH

Tel: +44 (0)161 868 7600 Fax: +44 (0)161 868 7699 Registered Office:

i54 Business Park, Valiant Way Wolverhampton, WV9 5GB Registration Number: 7401660 Vat Number: 887 1276 83



Page 2 of 4

Appendix 1 to report no: AR-17-JR-013742-02

Sample no: 799-2017-00109892

#### Photo:





Appendix 1 to report no: AR-17-JR-012337-01

Sample no: 799-2017-00108135

Page 3 of 4

### JR0EP - EN 71-3:2013 + A1:2014 Safety of Toys - Migration of certain 19 elements (##)

Limits of element migration from accessible parts of toy material All figures quoted as mg soluble element per kg material

Element		В	Al	Cr(III) Cr(VI)	Mn	Со	Ni	Cu	Zn	As	Se	Sr	Cd	Sn	Organic tin	Ва	Hg	Pb	Sb
Limits Category I mg/kg (dry, brittle, powder like, pliable)		1200	5625	37,5 0,02	1200	10,5	75	622,5	3750	3,8	37,5	4500	1,3	15000	0,9	1500	7,5	13,5	45
Limits Category II mg/kg (liquid, sticky)		300	1406	9,4 0,005	300	2,6	18,8	156	938	0,9	9,4	1125	0,3	3750	0,2	375	1,9	3,4	11,3
Limits Category III mg/k (scraped-off)		15000	70000	460 0,2	15000	130	930	7700	46000	47	460	56000	17	180000	12	18750	94	160	560
Description of sample		Results of analysis																	
Α	Play sand Cat I⊠ Cat II□ Cat III□	0,17	190	0,3	93	0,35	0,59	1,1	<0,25*	0,14	<0,5*	17	<0,05*	<0,08*	<0,9	16	<0,05*	0,6	<0,25*

\* Limit of quantification

Chrom (VI): Metrohm: 930 Compact IC flex

## - Eurofins Consumer Product Testing (Hamburg) is accredited for this test except for Cr (III) and Cr (VI)

Test results and evaluation relate to the tested items only.

Tested by: KBe Date: 2017-07-11



Appendix 1 to report no: AR-17-JR-012337-01

Sample no: 799-2017-00108135

Page 4 of 4

### Analytical details (EN 71-3 clause 10)

- 10f Technique used: Inductively coupled plasma
- 10h Notes for individual sample portions the following notes apply to the samples indicated and referenced above:

	Applicable samples:
Between 10 and 100mg taken:	
Sample/volume ratio exceeds 1:50:	
Base material included:	
Samples sieved:	
2M HCl added:	
6M HCl added:	
n-heptane used:	
Samples centrifuged:	
Specimens adjusted to 0.3M:	
Less than 10mg present:	
Others:	

\*\*\*END OF REPORT\*\*\*